

Neath Jointing Rake out and Replace

Location – Span 1 Abutment

Before Picture



Mortar Used as per NWR Standard – NR/CV/SD/101

MORTAR

- f) MORTAR USED FOR RE-CASING SHALL BE AS FOLLOWS:- 1: 1/4: 4 CEMENT/LIME/SAND WITH THE ADDITION OF AN APPROVED AIR ENTRAINING AGENT TO ENHANCE FROST RESISTANCE.
CEMENT FOR MORTAR SHALL BE "PORTLAND" COMPLYING WITH BS 12.
LIME SHALL BE HIGH CALCIUM LIME, SEMI-HYDRAULIC LIME OR MAGNESIUM LIME COMPLYING WITH BS EN 459-1.
SAND SHALL COMPLY WITH BS EN 1313 AND SHALL BE WASHED SAND OR NATURAL-CRUSHED ROCK. IT SHALL NOT BE OF A MARINE SOURCE.
WATER SHALL NOT CONTAIN IMPURITIES & BE TESTED IN ACCORDANCE WITH BS EN 1008.
BATCHED MIXES SHALL BE USED UP WITHIN 2 HOURS OF MIXING.

#

After Picture

