

Yorkstone Play Tower Technical Data Sheet

Product Code:
S35-105-A

Stone Classification
Sandstone

Source
Yorkshire-England 



Please note:

Sawn tonality variation and finish; Natural variations may occur between image and finished product.

0 mm 5

Project Shot:

Yorstone play tower.



Test	Value	BS EN
Apparent density (g/cm ³)	2.44	1936
Water Absorption (%)	2.19	13755
Abrasion Resistance (mm)	16.5	14157
Flexural Strength (Mpa) LEV	11.9	12372
Flexural Strength (Mpa) Mean	15.0	12372
Flexural freeze thaw (Before/After)	15.0/13.0	12371
Compressive Strength (Mpa) LEV	79.29	1926
Compressive Strength (Mpa) Mean	118	1926
Compressive freeze thaw (Before / After)	79.26/78.3	12371
USRV Sawn Dry/Wet	95/84	14231
USRV Shot Sawn Dry/Wet	99/85	14231
Open Porosity (%)	7.53	1936

British Standards:

Paving, Setts and Kerbs are CE marked to BS EN 1341, 1342 and 1343.

Tolerances:

Stone dimensions are produced to meet class 1 specification as a minimum.

Quality Control:

Stone supplied in accordance with ISO 9001 quality standards.

Maintenance:

Clean warm water with natural soap would be the most common method of cleaning the stone.

We also offer a wide range specialist cleaning products and impregnators. Please contact our technical department for any further information.

*Inspiring beautiful
landscapes*